



FR-Jersey-200

60% MODACRYLIC PROTEX /
39% VILOFT / 1% AS

200 GSM / knitted fabric



Fabric name	FR-Jersey-200
Fabric weight	200 g/m ² ± 5%
Composition	60% Modacrylic Protex, 39% Viloft, 1% Antistatic
Full width	160 cm
Weave	knitted fabric
Finishes	-
Application	Thermal Clothing
Washing instruction	

FR & SPECIAL PROPERTIES

Flame retardant	ISO 11612:2015 (A1, A2, B1, C1)	ISO 14116
Anti static	EN 1149-5:2018	

PHYSICAL PROPERTIES

Bursting resistance	ISO 13938-1:1999	190.5 KPa
Dimensional Stability To Washing, max	ISO 5077- ISO 6330	<5 %

COLOUR FASTNESS

			Light	Mid	Dark	Special colors
			Orange, Yellow	Green, Grey, Royal Box	Dark Navy, Navy, Royal Blue	Black
Wash Fastness Method E2S (95°C)	ISO 105-C06	Colour Change	4-5	4-5	4-5	4-5
		Stain on Polyester	3-4	4	4-5	3
		Stain on Cotton	4	4-5	4-5	3-4
Rub Fastness	ISO 105-X12:1995	Wet	3-4	3-4	3	3
		Dry	4-5	4-5	4-5	3-4
Light Fastness	ISO 105-B02		3	3-4	4	4