



Flame Retardant fabric for FR-clothing

Murano-250

60% MODACRYLIC / 35% COTTON

4% NYLON / 1% AS

250 GSM / RIPSTOP



Fabric name	Murano-250
Fabric weight	250 g/m ² ± 5%
Composition	60% Modacrylic, 35% Cotton, 4% Nylon, 1% Antistatic
Full width	150 cm
Weave	Ripstop
Finishes	Flame Retardant, MR (Multi-Risk)
Application	FR-clothing
Washing instruction	

FR & SPECIAL PROPERTIES

Flame retardant	EN ISO 11612:2015 (A1 & A2,	EN 13034	EN ISO 11611 (class 1)
Antistatic	EN 1149-5 (1149-3 method 2) IEC 61482-1-1 ATPV 6.9 cal/cm ² , ELIM 6,5 cal/cm ²		

PHYSICAL PROPERTIES

		warp	weft
Tensile strength, N	ISO 13934-1:1999	800 N	600 N
Tearing strength, N	ISO 13937-2:2000	40 N	30N
Dimensional Stability To Washing, max.	ISO 5077-ISO 15797	<3%	
Abrasion Resistance	ISO 13934-1:1994	21 000 rubs	
Pilling Resistance	ISO 12947-2:1999	4	

COLOUR FASTNESS

			Light	Mid	Dark	Special colors
			Orange, Yellow	Green, Grey, Royal Box	Dark Navy, Navy, Royal Blue	Black
Wash Fastness Method E2S (95°C)	ISO 105-C06	Colour Change	4-5	4-5	4-5	4
		Stain on Polyester	4-5	4-5	4-5	4
		Stain on Cotton	4	4-5	4-5	3-4
Rub Fastness	ISO 105-X12:1995	Wet	3	3	3	2-3
		Dry	4	4	4	4
Light Fastness	ISO 105-B02		3	3-4	4	4

XM Textiles Europe
 Email: info@xmtextiles.com
 www.xmtextiles.com

Darius ir Gireno st. 42A Office 509
 Vilnius LT – 02189 Lithuania
 Tel: +370 (347) 20299

Sos.Tamasi 20, Hala 3A, et. 1
 Buftea (platforma Rombiz), Romania
 Zip 070000, Tel: +40 31 630 36 39